



## Suprem EVA Industries Sdn Bhd.

EPDM  
Opened Cell

SP-1130

Document No.

Version

Number of Page

1

### Technical Data Sheet

#### Product Construction

**Product Series**

**Color**

**Standard size**

EPDM

Black

1000mm x 2000mm

SP-1130

#### Relative Data

Note: The following data obtained from MX lab according to related test standard, should be considered as typical property but not for specification purposes.

Item	Data	Test Method
Density (kg/m <sup>3</sup> )	130±20	ASTM D3574
Tensile Strength (Mpa)	≥0.08	ASTM D412
Elongation Rate (%)	≥150	ASTM D412
Tearing Strength (kn/m)	≥0.6	ASTM D624
Water Absorption (%)	≤10	ASTM1056
Compression Deflection (25%, 22hrs at 70°C, rebound in 30min) (%)	≤20	ASTMD395
Shrinkage (70°C, 24HRS) (%)	≤1	ISO 188
High Temperature Resistance (90°C, 2HRS) (%)	≤1%	ASTM D1056
Ozone Aging Testing (50°C 3HRS, concentration 50ppm)	No Fracture	
Rate of Flame Retardant	Burning Speed Rate ≤80	FMVSS302 UL94

Product physical report to our test data shall prevail.

End Mark